

WÜKOSEAL® 604

TECHNICAL INFORMATION

Application: Waterborne dispersion for coatings of paper, cardboard, glass and aluminium foils.

Properties and advantages:

- Strong water resistance
- Good water vapour resistance
- Emulsifier free
- By sufficient drying a stiff transparent film is achieved, which is sealable against itself and aluminium foil

Technical data:

Appearance:	white opaque
Base:	ethylene-copolymer
Active content:	35.0 + 1.0 %
pH-value:	8.0 + 1.0
Viscosity (DIN 4 mm cup):	10 – 25 s

Recommended dosage:

Application system:	roller coating or air-brush
Application quantity:	3 – 10 g/m ²
Drying:	100 – 160 °C depending on equipment

The dispersion can be diluted with deionised water.
If you formulate our product please make sure, that the pH-value of your additives is not below pH 8.

Transport and storage: Our dispersions are sensitive to frost and heat!
To be stored and transported between + 5° C and + 35° C.
Maximum storage time 6 months in originally closed packaging.

Packaging: Drums with 150 kg
Containers with about 1.000 kg