

CERETAN[®] A 70

TECHNICAL INFORMATION

Chemical description: Ethylene-bis-Stearamide- wax [EBS]

Application: **Paints and coatings**, e.g. powder coatings
Masterbatch, e.g. polycarbonate, polystyrol and PVC
Lubricants

Properties:

- Release- and antiblocking agent for Polyolefin- flow distribution
- Internal lubricant- and antiblocking agent

Advantages:

- Temperature stability

Technical data:

Colour:	yellowish		
Consistency:	fine granules		
	Minimum	Maximum	Method
Drop point*:	143 °C	151 °C	LV 12 (DGF M-III 3)
Viscosity (150°C):	20 mPas	40 mPas	LV 2 (DIN EN ISO 3104)
Penetration:		1,0 mm*10 ⁻¹	LV 4 (DIN 51579)
Acid value*:	4 mg KOH/g	6 mg KOH/g	DIN EN ISO 2114
Shelf life:	24 months (Stored in sealed original packing below 35 °C)		

* part of certificate of analysis

Our technical suggestions are based on data from many experiments and cannot represent a warranty of any kind as to their performance in other formulations. Customers must always verify our product's performance in their own systems. This technical data sheet replaces all previous issues.
EN Revision: October 2018